

# T & R WILLIAMSON LTD

A DIVISION OF THOMAS HOWSE LTD

## TRANSPPEED RANGE

## SEMI-GLOSS TRANSPORT FINISH

CAT NO: 03087

T D NO: 129



By Appointment  
to HM The Queen  
T&R Williamson Ltd  
Manufacturers  
of Coatings and Paints Ripon

## TECHNICAL DATA SHEET

T & R Williamson Ltd, Ripon HG4 1TP

enquiries@trwilliamson.co.uk

T: 01765607711

F: 01765607908

Revised: 2021

### PRODUCT FEATURES

Principally intended for application by brush, it can, if required be applied by spray.

### THEORETICAL VOLUME SOLIDS:

50%

### POT LIFE OF MIXTURE:

N/A

### FLASH POINT:

Above 32°C

### VOCs PER LITRE:



On average  
300-400g/litre.  
(Depending on colour.)

2004/42/II B(d)420 The EU limit for this product category IIB(d) in ready to use form is a maximum of 420g/Litre.



### DESCRIPTION

Transpeed Semi Gloss finish is a one component product formulated on an air drying urethane modified alkyd. Specially formulated to combine good flow and high opacity with a semi-gloss finish.



### SURFACE PREPARATION

**Substrates:** Recommended for use directly over any of the following products:

Transpeed Fleetprime: 116 spray

Transpeed Anti Corrosive Primer: 102 brush or spray

Transpeed Undercoat: 103 brush or spray

Previously painted surfaces in sound condition and suitably prepared

Ensure all surfaces are clean, dry and free from contaminants such as oil grease, silicone etc.

If required, primers and undercoats can be lightly denibbed using P600 grade paper or Scotchbrite.

Tac rag to remove dust before over-coating.

Previously painted surfaces must be abraded with P360 - P400 grade wet or dry or machine sanded using P220 - P320 grade grit discs to provide a matt keyed surface. Finally spirit wipe before painting.



### Preparation:

Ensure all surfaces to be undercoated are clean, dry and free from contaminants such as oil, grease, silicon, etc

### MIXING RATIO\*

This is a one pack product. No mixing Required



\*All pigmented fluid paints have a tendency to settle and separate over a period of time. In order to ensure that the paint is evenly dispersed before use it is essential that the material in the can is thoroughly hand stirred after opening. In difficult circumstances, the use of a mixing machine or mechanical stirrer will be more effective.

### SPRAYING VISCOSITY

22 - 25 Seconds *	reduce as necessary *
Conventional	Airless

\*In a 4mm Flow Cup. (Spraying viscosity and thinning will depend on ambient conditions, spray equipment used and desired finish.)

## SHELF LIFE

12 months from the date of manufacture, stored in original unopened container at a temperature between 10°C and 25°C

## SPREAD RATE:

Approx. 20 m<sup>2</sup>/litre dependant upon application

## EWC CODE:

08 01 11



## METHODS OF APPLICATION

Method:	Brush	Conventional Spray	HVLP
Thinning:	N/A	Up to 5% Thinners SR 25	
Fluid :	N/A	Pressure feed	
Spray Gun Fluid Tip:	N/A	1.4 - 1.8mm	FF 1.4mm
Spray Gun Needle:	N/A	FF/EX	FF
Spray Gun Air Cap:	N/A	30	13
Air Pressure at the Gun:	N/A	55-60 psi (3.8-4.2 bar)	25 psi (1.7 bar)
Pressure at Aircap:	N/A	N/A	10 psi (0.7 bar)
Number of coats:	1 full coat	Light coat – full coat to required thickness	



## THINNERS

Up to 5% Special Thinners 36625SR025



## DRYING TIMES

5-6 hours Touch Dry, 16 hours Hard Dry



## RECOMMENDED FILM THICKNESS

Wet Film Thickness	50 Microns
Dry Film Thickness	25 Microns



## CLEANING

Equipment Cleaning using Williamsons SR1 Thinners or Gunwash